

TVIS™ PREMIUM THIN VENEER BONDING MORTAR

1. Product Name

TVIS Premium Thin Veneer Bonding Mortar

2. Manufacturer

Custom Building Products
13001 Seal Beach Blvd.
Seal Beach, CA 90740-2757
Customer Support: 800-272-8786
Technical Services: 800-282-8786
Fax: 800- 200-7765
Email: contactus@cbpmail.net
custombuildingproducts.com

3. Product Description

TVIS Premium Thin Veneer Bonding Mortar is a premium pre-blended polymer-modified mortar for use with thin veneer, large tile and natural stone. With a non-slip formula to eliminate slipping, Premium Thin Veneer Bonding Mortar can be applied to 3/4" (19 mm) thick for medium bed applications. Use it for vitreous, semi-vitreous and absorptive veneers, including thin brick, pavers, gauged or ungauged natural stone and precast terrazzo.

When mixed with water, TVIS Premium Thin Veneer Bonding Mortar can be used with the following

- Interior and exterior thin veneer installations
- Concrete, mortar beds, masonry
- WonderBoard®, cement backerboards

When mixed with TVIS SBR Masonry Mortar Admix, TVIS Premium Thin Veneer Bonding Mortar can be used with

- Exterior grade plywood (interior residential and light commercial dry areas)
- Waterproofing membranes, such as TVIS Veneer Waterproofing Membrane

COMPOSITION & MATERIALS


TVIS Premium Thin Veneer Bonding Mortar is a Portland cement based mortar.

BENEFITS

- Designed for thin brick, thin veneers and for large dimensional stone and tile to 12" x 12" (30 x 30 cm)
- Can be applied to 3/4" (19 mm) thick
- Meets ANSI A118.4 without the need for additives; Meets ANSI A118.11 with the addition of TVIS SBR Masonry Mortar Admix

Accessories

TVIS SBR Masonry Mortar Admix is an additive available for use with TVIS Premium Thin Veneer Bonding Mortar to improve bond strength and increase tensile and compressive strength.



LIMITATIONS

- Do not bond directly to metal, fiberglass, plastic or OSB panels.
- When setting moisture sensitive natural stone, cement or agglomerate tile, check with Technical Services; use EBM-Lite™ Epoxy Bonding Mortar.
- Do not use to install resin-backed stone, use EBM-Lite Epoxy Bonding Mortar.
- When setting dimensional stone larger than 12" x 12" (30 x 30 cm) contact Technical Services for recommendations regarding deflection requirements.

PACKAGING

- 50 lbs (22.68 kg) bag
- Gray

4. Technical Data

APPLICABLE STANDARDS

TVIS Premium Thin Veneer Bonding Mortar is compliant with the following:

- American National Standards Institute (ANSI) – ANSI A108.5, A118.4, A118.11.
- ASTM C91 Standard Specification for Masonry Cement
- ASTM C144 Standard Specification for Aggregate for Masonry Mortar, as a component of the manufactured mortar.
- ASTM C150 Standard Specification for Portland Cement, as a component of the manufactured mortar
- ASTM C207 Standard Specification for Hydrated Lime for Masonry purposes, as a component of the manufactured mortar.



- ASTM C1072 Standard Test Method for Measurement of Masonry Flexural Strength.
- ASTM C270 Standard Specification for Mortar with Masonry Units
- ASTM C109 Standard Test Method for Compressive Strength of Hydraulic Cement Mortars.

Tile Council of North America (TCNA) – TCNA Handbook for Ceramic Tile Installation

TECHNICAL PROPERTIES

| Property | Results |
|---|---------------------------------------|
| Pot life | 60 minutes |
| Open time | 35 minutes |
| Adjustment time | 35 minutes |
| Shear bond @ 28 days | |
| Bisque tile | 350 psi (24.6 kg/cm ²) |
| Porcelain Tile | 259 psi (24.6 kg/cm ²) |
| Compressive Strength @28 days 2" cube (50 mm) | Typical Value >2500 psi (175.7 kg/cm) |

ENVIRONMENTAL CONSIDERATIONS

Custom Building Products is committed to environmental responsibility in both products produced and in manufacturing practices.

The use of Custom TVIS Premium Thin Veneer Bonding Mortar may contribute to LEED® certification

5. Installation

PREPARATORY WORK

General Surface Preparation:

Surfaces must be structurally sound, clean, dry and free from grease, oil, dirt, curing compounds, sealers, adhesives and other contaminants that would prevent a good bond. Glossy or painted surfaces must be sanded, stripped and cleaned of waxes, dirt and other contaminants. Ambient temperature, surfaces and materials should be 50° – 100° F (10° – 38° C) for 72 hours.

Cementitious Surfaces:

Concrete or plaster must be fully cured and must accept water penetration. Test by sprinkling water on various areas of the substrate. If water penetrates, then a good bond can be achieved; if water beads, surface contaminants are present, and loss of adhesion may occur. Contaminants should be mechanically removed before installation. Concrete must be free of efflorescence and not subject to hydrostatic pressure. Concrete slabs should have a broomed or brushed finish to enhance the bond. Smooth concrete slabs must be mechanically abraded to ensure a good bond.

Lightweight, Gypsum Based Underlayments:

Lightweight or gypsum based underlayments must first be treated with TVIS Veneer Waterproofing Membrane and must obtain a minimum 2000 psi (13.8 MPa) compressive strength at the recommended cure time. The underlayment must be sufficiently dry and properly cured to the manufacturer’s specifications for permanent, non-moisture permeable coverings. Surfaces must be structurally sound and subject to deflection not to exceed the current ANSI standards.

All lightweight concrete and gypsum based underlayment surfaces to receive Veneer Waterproofing Membrane must be primed with properly applied sealer or a primer coat of Veneer Waterproofing Membrane, consisting of 1 part Veneer Waterproofing Membrane diluted with 4 parts clean, cool water. Mix in a clean bucket at low speed to obtain a lump free solution. The primer can be brushed, rolled or sprayed to achieve an even coat. Apply the primer coat to the floor at a rate of 300 ft² / gal (7.5 M² / L). Drying time depends on site conditions, but is normally less than 1 hour. Extremely porous surfaces may require 2 coats. At this point, Veneer Waterproofing Membrane can be applied to the primed lightweight or gypsum based surface. Refer to the individual technical data sheet or packaging directions for application instructions.

Plywood Substrates:

Plywood substrates must be structurally sound and must meet all local building codes and ANSI deflection requirements. For questions and proper substrate installations, contact Technical Services.

WonderBoard Backerboard:

As an alternative to an additional layer of plywood, WonderBoard backerboard may be used.

Expansion Joints:

Expansion joints, control joints and cold joints should never be bridged with setting material. They must be brought through the finished masonry work and filled with an approved elastomeric sealant.

METHODS

Mixing

Mix 5 quarts (4.73 L) clean water per 50 lbs (22.68 kg) of mortar. For added bond strength and flexibility mix 5 quarts (4.73 L) of SBR Masonry Mortar Admix and 50 lbs (22.68 kg) powder together.

Mix by hand or use a low 150 – 200 rpm speed 1/2" (13 mm) drill to achieve a smooth, paste-like consistency. Let the mixture slake or stand 5 – 10 minutes; stir again and use. Stir occasionally, but do not add more water. When properly mixed, troweled ridges will stand without slump.



Application

Use a properly sized notch trowel to ensure proper coverage behind the thin brick or tile veneer. Using the flat side of the trowel, apply a skim coat of mortar to the surface. With the notched side of the trowel held at a 45° angle, apply additional mortar to the surface, combing in one direction. Press the thin brick or veneer firmly into place in a perpendicular motion across ridges, moving back and forth. The perpendicular motion flattens ridges and closes valleys, allowing maximum coverage. Back buttering is advised. Adjust the masonry promptly and beat it in with a block and rubber mallet. Periodically check the back to ensure proper adhesive coverage. Do not spread more material than can be covered within 10 minutes or while material has a wet tack (sticky to the touch). If the material has skinned over (not sticky), re-comb with the notch trowel; if too dry, remove and replace the dry material with fresh material. Material in the bucket will remain workable for approximately 2 hours.

Coverage

| SQUARE FOOT COVERAGE PER 50 LB BAG (SQUARE METER PER 22.68 KG) | |
|---|--|
| TROWEL SIZE | COVERAGE |
| 1/2" x 1/2" x 1/2" (13 x 13 x 13 mm) Square-Notch | 43 – 48 sq. ft. (4 – 4.5 M ²) |
| 3/4" x 9/16" x 3/8" (19 x 14 x 9.5 mm) U-Notch | 34 – 38 sq. ft. (3.2 – 3.5 M ²) |

Curing

Allow to cure 24 hours before filling joints with Custom TVIS Premium Veneer Pointing Mortar, depending upon temperature and humidity.

Cleaning

Clean with water before the material dries.

PRECAUTIONS

This product contains Portland cement and free silica. Avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. If eye contact occurs, flush with water for 15 minutes and consult a physician. Do not breathe dust; wear a NIOSH approved respirator

BUILDING CODES

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

6. Availability & Cost

Contact the manufacturer or visit customTVIS.com for information about product cost and availability.

| ITEM CODE | SIZE | PACKAGE |
|-----------|-------------------|---------|
| TTVMB50 | 50 lbs (22.68 kg) | Bag |

7. Limited Product Warranty

Eligibility for Installation Systems Warranty

This product may be eligible for a Custom Building Products Installation Systems Warranty of up to 15 years, provided our products are used as a complete installation system.

Custom Building Products warrants to the original consumer purchaser that its product shall be free from defects in material and workmanship under normal and proper usage for a period of one year following the date of original purchase. Custom’s sole liability under this warranty shall be limited to the replacement of the product. Some states, countries or territories do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty will not extend to any product which has been modified in any way or which has not been used in accordance with Custom’s printed instructions. Custom makes no other warranties either expressed or implied. This warranty gives you specific legal rights, and you may have other rights that vary from state to state or from one country/territory to another.

For details and complete warranty information, contact Custom Building Products or visit customTVIS.com.

8. Maintenance

Properly installed product requires no special maintenance.

9. Technical Services

For technical assistance, contact Custom Building Products or visit customTVIS.com.

10. Filing Systems

Additional product information is available from the manufacturer upon request.

Related Products

TVIS Premium Veneer Pointing Mortar

LEED is a Registered Trademark of U.S.G.B.C.

